

PATENT

Case Docket No.: NOVCEL.3CPDDVC

Filing Date: January 20, 2004

Applicant(s) : **Hubbell, et al.**  
App. No. : **10/761,180**  
Filed : **January 20, 2004**  
For : **Gels For Encapsulation Of  
Biological Materials**  
Examiner : **Berman, Susan W.**  
Group Art Unit : **1711**

I hereby certify that this correspondence and all marked attachments are being deposited with the United States Postal Service as first class mail in an envelope addressed to: Mail Stop Amendment, Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450, on

March 1, 2006

(Date)  
  
Kirk Hahn, Reg. No. 51,763

## DECLARATION UNDER 37 C.F.R. §1.131

Commissioner for Patents  
P.O. Box 1450  
Alexandria, VA 22313-1450

Sir:

1. I, AMARPREET S. SAWHNEY, a citizen of the United States, hereby declare that:

2. My address is 101A First Ave., Waltham, MA 02451.

3. I am a co-inventor of the invention in U.S. Application Serial No. **10/761,180** entitled "**Gels For Encapsulation Of Biological Materials**" (the "Application"); and U.S. Application Serial No. 07/843,485 ("Priority Document I"), now abandoned, filed February 28, 1992 and U.S. Application Serial No. 07/870,540 ("Priority Document II"), filed April 20, 1992, now abandoned, on which this application claims priority.

4. I understand that the Examiner has cited Soon-Shiong et al., U.S. Patent Numbers 5,700,848; 5,705,270 and 5,846,530 in her rejection of the claims presented in the Application. I also understand that Soon-Shiong '848, '270 and '530 have effective filing dates of October 29, 1991.

5. Prior to October 29, 1991; I reduced to practice in the United States a method of encapsulating biological materials, which comprises mixing the biological material with a polymer, forming microcapsules, coating the microcapsules with a photoinitiator, mixing the microcapsules containing the biological material in an aqueous macromer, polymerizing the gel using a light source, and generating macrocapsules in accordance with the subject matter claimed

in this application.

6. Attached hereto is a copy of a page from my laboratory notebook ("Exhibit 1"), which shows a protocol for encapsulating cells in alginate-PLL microcapsules. Except for the masked date, Exhibit 1 is a true and correct copy of the relevant page in the original bound laboratory notebook.

7. Attached hereto is a copy of a page from my laboratory notebook ("Exhibit 2") bearing a date before October 29, 1991. Except for the masked date, Exhibit 2 is a true and correct copy of the relevant page in the original bound laboratory notebook. Exhibit 3 is a transcription of the handwriting of Exhibit 2.


8. Exhibit 2 shows the protocol for encapsulating alginate-PLL microcapsules in a photopolymerized PEO gel. The steps in the protocol correspond to the steps in the application.

9. Accordingly, Exhibit 1 and Exhibit 2 demonstrate that the invention as described in the Application was conceived and reduced to practice in the United States before the filing date of Soon-Shiong '848.

10. I understand that the Examiner has also cited Soon-Shiong et al., U.S. Patent Numbers 5,545,423; 5,759,578; 5,788,988 and 5,879,709 in her rejection of the claims presented in the Application. I understand that Soon-Shiong '423, '578, '988, and '709 have effective filing dates of November 25, 1991, which is later than Soon-Shiong '848. Therefore, as shown above, the invention was conceived and reduced to practice in the United States before the effective filing date of Soon-Shiong '423.

11. I further declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true. Moreover, these statements were made with the knowledge that willful false statements are punishable by fine or imprisonment, or both, under 18 U.S.C. 1001, and that such willful false statements may jeopardize the validity of the application or any patents issued thereon.

2/22/06  
Date: \_\_\_\_\_

  
\_\_\_\_\_  
Amarpreet S. Sawhney

## **EXHIBIT 1**

Preliminary

## Procedure for Microencapsulation

A syringe pump with a 10-ml syringe connected to a special air jet is used for making sodium alginate islet droplets.

For each preparation, 2000-3000 islets in 0.2 ml of saline is mixed gently with 2 ml of 1.5% sodium alginate, transferred to the 10-ml syringe, and connected to the air jet. The distance from the tip of the air jet needle to the surface of the collecting fluid is set at precisely 8 cm. The syringe pump and air flow are then turned on to extrude sodium alginate droplets containing islets into 50 ml of the 1.1%  $\text{CaCl}_2$  solution in a beaker. During extrusion, the islets are kept in suspension by gently rotating a small magnet inside the 10-ml syringe. After the extrusion process is completed, the spherical calcium alginate gel droplets are transferred to a 50-ml polystyrene test tube with a conical bottom, and allowed to settle before withdrawing the supernatant down to 5 ml using a vacuum aspirator. The gel droplets are washed once with 30 ml of 0.55%  $\text{CaCl}_2$ , once with 0.25%  $\text{CaCl}_2$ , and then suspended in 25 ml of 0.1% CHES solution for 3 min. After aspirating the CHES solution, the capsules are washed with 1.1%  $\text{CaCl}_2$  and suspended in 25 ml of 0.05% (W/V) poly(L-lysine) for 6 min. After further washing with CHES,  $\text{CaCl}_2$ , and saline, the microcapsules are incubated in 0.15% sodium alginate for 4 min and washed with saline. The capsules are then suspended in 10 ml of 55 mM sodium citrate solution for 5 min. The final product is washed twice with saline and once with medium CMRL-1969, and then transferred to Falcon flasks for incubation at 37° until required for *in vitro* and *in vivo* studies.

distance  
should be  
8 cm

1. 1.1%  $\text{CaCl}_2$   
2. 0.25%  $\text{CaCl}_2$   
3. 0.1% CHES  
4. 1.1%  $\text{CaCl}_2$   
5. 0.05% poly(L-lysine)  
6. 0.1% CHES  
7. 0.15% sodium alginate  
8. 55 mM sodium citrate  
9. 1.1%  $\text{CaCl}_2$   
10. 0.1% CHES  
11. 0.1% CHES  
12. 0.1% CHES  
13. 0.1% CHES  
14. 0.1% CHES  
15. 0.1% CHES  
16. 0.1% CHES  
17. 0.1% CHES  
18. 0.1% CHES  
19. 0.1% CHES  
20. 0.1% CHES  
21. 0.1% CHES  
22. 0.1% CHES  
23. 0.1% CHES  
24. 0.1% CHES  
25. 0.1% CHES  
26. 0.1% CHES  
27. 0.1% CHES  
28. 0.1% CHES  
29. 0.1% CHES  
30. 0.1% CHES  
31. 0.1% CHES  
32. 0.1% CHES  
33. 0.1% CHES  
34. 0.1% CHES  
35. 0.1% CHES  
36. 0.1% CHES  
37. 0.1% CHES  
38. 0.1% CHES  
39. 0.1% CHES  
40. 0.1% CHES  
41. 0.1% CHES  
42. 0.1% CHES  
43. 0.1% CHES  
44. 0.1% CHES  
45. 0.1% CHES  
46. 0.1% CHES  
47. 0.1% CHES  
48. 0.1% CHES  
49. 0.1% CHES  
50. 0.1% CHES  
51. 0.1% CHES  
52. 0.1% CHES  
53. 0.1% CHES  
54. 0.1% CHES  
55. 0.1% CHES  
56. 0.1% CHES  
57. 0.1% CHES  
58. 0.1% CHES  
59. 0.1% CHES  
60. 0.1% CHES  
61. 0.1% CHES  
62. 0.1% CHES  
63. 0.1% CHES  
64. 0.1% CHES  
65. 0.1% CHES  
66. 0.1% CHES  
67. 0.1% CHES  
68. 0.1% CHES  
69. 0.1% CHES  
70. 0.1% CHES  
71. 0.1% CHES  
72. 0.1% CHES  
73. 0.1% CHES  
74. 0.1% CHES  
75. 0.1% CHES  
76. 0.1% CHES  
77. 0.1% CHES  
78. 0.1% CHES  
79. 0.1% CHES  
80. 0.1% CHES  
81. 0.1% CHES  
82. 0.1% CHES  
83. 0.1% CHES  
84. 0.1% CHES  
85. 0.1% CHES  
86. 0.1% CHES  
87. 0.1% CHES  
88. 0.1% CHES  
89. 0.1% CHES  
90. 0.1% CHES  
91. 0.1% CHES  
92. 0.1% CHES  
93. 0.1% CHES  
94. 0.1% CHES  
95. 0.1% CHES  
96. 0.1% CHES  
97. 0.1% CHES  
98. 0.1% CHES  
99. 0.1% CHES  
100. 0.1% CHES

1400 mL | mix on test tube on wall (air-pressure)

## **EXHIBIT 2**

PROTOCOL FOR PLL-MICROSPHERES COATING W/ PEO GELS

Make slurry of PLL microspheres & immerse them in a saturated (freshly made) solution of ethyl eosin in a HEPES buffered saline. Aspirate off all excess &  $\text{CaCl}_2$  sol<sup>n</sup> from spheres & add 10 ml of dye sol<sup>n</sup>. Incubate for 5 min. Rinse off repeatedly (about 4-5 times) w/ 1.1%  $\text{CaCl}_2$ .

Aspirate 0.5 ml spheres into 15 ml centrifuge tubes. Aspirate off all excess & spin. Add 100  $\mu\text{l}$  of TEA sol<sup>n</sup> ( ) and add 2 ml of 30% PEO aqueous sol<sup>n</sup>s. Vortex & expose to laser (514 nm) at ~100 mW for ~1-2 min with ~~add~~ intermittent stirring. Add 10 ml saline to wash off excess polymer, aspirate & incubate w/ citrate sol<sup>n</sup> to allow spheres to reswell. Wash twice w/ citrate & then w/ saline. Suspend in 5 ml saline & implant in 2 mice.

## **EXHIBIT 3**

### EXHIBIT 3

#### Transcription of handwriting of Exhibit 2

#### PROTOCOL FOR PLL-MICROSPHERE COATING W/ PEO GELS

Make algin -/PLL microspheres & immerse them in a saturated (freshly made) solution of ethyl eosin in HEPES buffered saline. Aspirate of<sup>1</sup> all excess  $\text{CaCl}_2$  sol<sup>2</sup> from spheres (5 ml) and add 10 ml of dye sol<sup>2</sup>. Incubate for 5 min. Rinse off repeatedly (about 4 – 5 times) w/- 1.1%  $\text{CaCl}_2$ .

Aliquot 0.5 ml spheres into 15 ml centrifuge tubes. Aspirate off all excess fluid. Add 10  $\mu\text{l}$  of  $\text{TEA}$ <sup>3</sup> sol<sup>2</sup> ( ) and add 2 ml of 30%  $\text{PEO}$ <sup>4</sup> acrylate sol<sup>2</sup>'s. Vortex & expose to laser (514 nm) at ~100 mW for ~1-2 min with intermediate stirring. Add 10 ml saline to wash off excess polymer, aspirate & incubate w/- citrate sol<sup>2</sup> to allow spheres to re-swell. Wash twice w/- citrate and then w/- saline. Suspend in 5 ml saline & implant in 2 mice.

\*\*\*\*\*

<sup>1</sup> "of" is off

<sup>2</sup> "sol<sup>2</sup>" is solution

<sup>3</sup> "TEA" is triethanol amine

<sup>4</sup> "PEO" is poly(ethylene oxide)